# DIAION<sup>™</sup> PA312L

DIAION $^{\text{TM}}$  PA312L is a porous type strongly basic anion exchange resin. It has a 6% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing pure water and waste water treatment, is recommended.

| P | ro | d | u | C. | t |
|---|----|---|---|----|---|
|   |    | v | v | ·  | · |

| Grade Name              | DIAION <sup>TM</sup> PA312L        |  |
|-------------------------|------------------------------------|--|
| Туре                    | Strong Base Anion                  |  |
| Matrix                  | Styrene-DVB, Porous                |  |
| Functional Group        | Type I (trimethyl ammonium groups) |  |
| Ionic Form              | Cl                                 |  |
| Specification           |                                    |  |
| Whole Bead Count        | - 95 min.                          |  |
| Salt Splitting Capacity | meg/mL 1.2 min.                    |  |

| Whole Bead Count                            | =      | 95 min.   |
|---|--------|-----------|
| Salt Splitting Capacity                     | meq/mL | 1.2 min.  |
| Water Content                               | %      | 49 - 55   |
| Particle Size Distribution on 1180 μm       | %      | 5 max.    |
| Particle Size Distribution thr. 425 $\mu m$ | %      | 5 max.    |
| Effective Size                              | mm     | 0.45 min. |
| Uniformity Coefficient                      | -      | 1.6 max.  |

### **Typical Properties**

| Shipping Density          | g/L  | 680  |
|---------------------------|------|------|
| Mean Particle Size        | μm   | 660  |
| Particle Density          | g/mL | 1.07 |
| Total Swelling (Cl to OH) | %    | 23   |

## **Recommended Operating Conditions**

| Maximum Operating Temperature | °C  | 80 (CI <sup>-</sup> ) |
|-------------------------------|-----|-----------------------|
|                               |     | 60 (OH <sup>-</sup> ) |
| Operating pH Range            |     | 0 - 14                |
| Minimum Bed Depth             | mm  | 800                   |
| Service Flow Rate             | m/h | 10 - 60               |
| Regenerant                    |     | NaOH                  |
| Regenerant Concentration      | %   | NaOH 2 - 8            |
| Regenerant Level              | g/L | 50 - 200              |
| Regenerant Flow Rate          | m/h | 2 - 8                 |
| Total Rince Requirement       | BV  | 2 - 10                |



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech

### **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> PA312L resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of PA312L




Fig. 2 Bed Expansion of PA312L

#### **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

