Product Data Sheet

DIAION[™] PA418

DIAION[™] PA418 is a porous type strongly basic anion exchange resin. It is type II resin and has a 9% cross-linkages. A wide range of applications, especially in a field of manufacturing pure water and waste water treatment, is recommended.


| Product | | |
|--|---|-----------------------|
| Grade Name | DIAION [™] PA418 | |
| Туре | Strong Base Anion | |
| Matrix | Styrene-DVB, Porous | |
| Functional Group | Type II (dimethylethanol ammonium groups) | |
| Ionic Form | Cl | |
| Specification | | |
| Whole Bead Count | - | 95 min. |
| Salt Splitting Capacity | meq/mL | 1.3 min. |
| Water Content | % | 38 - 44 |
| Particle Size Distribution on 1180 μ m | % | 5 max. |
| Particle Size Distribution thr. 300 μm | % | 1 max. |
| Effective Size | mm | 0.40 min. |
| Uniformity Coefficient | - | 1.6 max. |
| Typical Properties | | |
| Shipping Density | g/L | 670 |
| Mean Particle Size | μm | 710 |
| Particle Density | g/mL | 1.11 |
| Total Swelling (Cl ⁻ to OH ⁻) | % | 11 |
| Recommended Operating Condit | ions | |
| Maximum Operating Temperature | °C | 60 (Cl ⁻) |
| | | 40 (OH ⁻) |
| Operating pH Range | | 0 - 14 |
| Minimum Bed Depth | mm | 800 |
| Service Flow Rate | m/h | 10 - 60 |
| Regenerant | | NaOH |
| Regenerant Concentration | % | NaOH 2 - 8 |
| Regenerant Level | g/L | 50 - 200 |
| Regenerant Flow Rate | m/h | 2 - 8 |
| Total Rince Requirement | BV | 2 - 10 |




Product Data Sheet DIAION[™] PA418

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of $DIAION^{TM}$ PA418 resin in normal down flow operation is shown in the graphs below.







Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech