## Product Data Sheet DIAION<sup>™</sup> PK228L

DIAION<sup>™</sup> PK228L is a porous type strongly acidic cation exchange resin. It has 14% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product Grade Name		DIAION <sup>™</sup> PK228L
Type Matrix		Strong Acid Cation
Functional Group		Styrene-DVB, Porous Sulfonic Acid
Ionic Form		
		Na
Specification		
Whole Bead Count	-	95 min.
Salt Splitting Capacity	meq/mL	2.05 min.
Water Content	%	37 - 43
Particle Size Distribution on 1180 $\mu m$	%	5 max.
Particle Size Distribution thr. 425 $\mu m$	%	1 max.
Effective Size	mm	0.45 min.
Uniformity Coefficient	-	1.6 max.
Typical Properties		
Shipping Density	g/L	810
Mean Particle Size	μm	730
Particle Density	g/mL	1.32
Total Swelling (Na <sup>+</sup> to $H^+$ )	%	5
Recommended Operating Condit	ions	
Maximum Operating Temperature	С°	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		HCI
		H <sub>2</sub> SO <sub>4</sub>
Regenerant Concentration	%	HCl 4 - 10
		H <sub>2</sub> SO <sub>4</sub> 1 - 4
Description	g/L	50 - 200
Regenerant Level		55 200
Regenerant Level Regenerant Flow Rate	m/h	2 - 10




Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech


## Product Data Sheet DIAION<sup>™</sup> PK228L

## Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of  $DIAION^{TM}$  PK228L resin in normal down flow operation is shown in the graphs below.







## Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech