## DIAION<sup>™</sup> SK1BLH

DIAION™ SK1BLH is a gel type strongly acidic cation exchange resin. It has standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

D	r۸	Ч		ct
г	w	u	u	u

Product					
Grade Name		DIAION <sup>TM</sup> SK1BLH			
Туре		Strong Acid Cation			
Matrix		Styrene-DVB, Gel			
Functional Group		Sulfonic acid			
Ionic Form		H <sup>+</sup>			
Specification					
Whole Bead Count	-	90 min.			
Salt Splitting Capacity	meq/mL	1.7 min.			
Water Content	%	50 - 60			
Particle Size Distribution on 1180 μm	%	5 max.			
Particle Size Distribution thr. 425 μm	%	1 max.			
Effective Size	mm	0.45 min.			
Uniformity Coefficient	-	1.6 max.			
Ionic Form Conversion (H <sup>+</sup> )	eq%	95 min.			
Typical Properties					
Shipping Density	g/L	790			
Mean Particle Size	μm	710			
Particle Density	g/mL	1.20			
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	9			
Recommended Operating Conditions					
Maximum Operating Temperature	°C	120			
Operating pH Range		0 - 14			
Minimum Bed Depth	mm	800			
Service Flow Rate	m/h	10 - 40			
Regenerant		HCI			
		$H_2SO_4$			
Regenerant Concentration	%	HCl 4 - 10			
		H <sub>2</sub> SO <sub>4</sub> 1 - 4			
Regenerant Level	g/L	30 - 150			
Regenerant Flow Rate	m/h	2 - 10			
=					

BV



**Total Rince Requirement** 

2 - 10

## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of  $\mathsf{DIAION}^\mathsf{TM}$  SK1BLH resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of SK1BLH




Fig. 2 Bed Expansion of SK1BLH

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

