DIAION™ UBK10 is a cation exchange resin with a uniform particle size. It has 10% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product	
Grade Name	DIAION <sup>™</sup> UBK10
Туре	Strong Acid Cation
Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid
Ionic Form	Na <sup>+</sup>

Specification		
Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	2.2 min.
Water Content	%	38 - 44
Mean Particle Size	μm	650 ± 50
Uniformity Coefficient	-	1.10 max.

Typical Properties		
Shipping Density	g/L	850
Particle Density	g/mL	1.32
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	8

Recommended Operating Condition	ons	
Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 40
Regenerant		HCI
		$H_2SO_4$
Regenerant Concentration	%	HCl 4 - 10
		H <sub>2</sub> SO <sub>4</sub> 1 - 4
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	2 - 10
Total Rince Requirement	BV	2 - 10



## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> UBK10 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK10




Fig. 2 Bed Expansion of UBK10



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech

## **Operational Capacity Data**




Fig. 3 Operational Capacity Data of UBK10
Regenerant: 4 % HCI

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.pyvot.tech