DIAION™ UBK12 is a cation exchange resin with a uniform particle size. It has 12% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

P	ro	d	u	ct
	$\cdot$	u	ч	·ι

Product		_			
Grade Name		DIAION <sup>TM</sup> UBK12			
Туре		Strong Acid Cation			
Matrix		Styrene-DVB, Gel			
Functional Group		Sulfonic acid			
Ionic Form		Na <sup>+</sup>			
Specification					
Whole Bead Count		90 min.			
Salt Splitting Capacity	meq/mL	2.3 min.			
Water Content	// //// // // // // // // // // // // /	33 - 39			
Mean Particle Size	μm	650 ± 50			
Uniformity Coefficient	-	1.2 max.			
Typical Properties					
Shipping Density	g/L	850			
Particle Density	g/mL	1.34			
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	6			
Recommended Operating Conditions					
Maximum Operating Temperature	°C	120			
Operating pH Range		0 - 14			
Minimum Bed Depth	mm	800			
Service Flow Rate	m/h	10 - 40			
Regenerant		HCI			
		$H_2SO_4$			
Regenerant Concentration	%	HCl 4 - 10			
		H <sub>2</sub> SO <sub>4</sub> 1 - 4			
Regenerant Level	g/L	30 - 150			
Regenerant Flow Rate	m/h	2 - 10			
Total Rince Requirement	BV	2 - 10			



## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> UBK12 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK12




Fig. 2 Bed Expansion of UBK12



## **Operational Capacity Data**




Fig. 3 Operational Capacity Data of UBK12

Regenerant: 4 % HCl

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

