

Product Data Sheet

DIAION™ UBK16

DIAION™ UBK16 is a cation exchange resin with a uniform particle size. It has 16% cross-linkages and excellent properties. A wide range of applications, especially in a field of pharmaceuticals, is recommended.

Product

Grade Name	DIAION™ UBK16
Type	Strong Acid Cation
Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid
Ionic Form	Na ⁺

Specification

Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	2.3 min.
Water Content	%	27 - 37
Mean Particle Size	μm	600 ± 50
Uniformity Coefficient	-	1.2 max.

Typical Properties

Shipping Density	g/L	870
Particle Density	g/mL	1.38
Total Swelling (Na ⁺ to H ⁺)	%	6

Recommended Operating Conditions

Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 40
Regenerant		HCl
		H ₂ SO ₄
Regenerant Concentration	%	HCl 4 - 10
		H ₂ SO ₄ 1 - 4
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	2 - 10
Total Rinse Requirement	BV	2 - 10



Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ UBK16 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK16




Fig. 2 Bed Expansion of UBK16

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

