

Product Data Sheet

DIAION™ USMN3

DIAION™ USMN3 is a nuclear grade mixed resin with strongly acidic cation exchange resin, DIAION™ UBKN1, with ⁷Li form and strongly basic anion exchange resin, DIAION™ UBAN1. It is used for cleanup system in primary circuit of PWR nuclear power plants.

Product

Grade Name	DIAION™ USMN3	
Type	Mixed	
Matrix	Styrene-DVB, Gel	
Functional Group	Sulfonic acid / Type I (trimethyl ammonium groups)	
Ionic Form	⁷ Li ⁺ / OH ⁻	
Chemical equivalent ratio	1 / 1	

Specification

Component	Cation exchange resin		Anion exchange resin
	DIAION™ UBKN1 (⁷ Li form)		DIAION™ UBAN1
Whole Bead Count	-	95 min.	90 min.
Salt Splitting Capacity	meq/mL	2.4 min.	1.2 min.
Average Diameter	µm	600 - 730	630 ± 50
Particle Size Distribution on 1180 µm	%	-	0.5 max.
Particle Size Distribution on 850 µm	%	0.5 max.	-
Particle Size Distribution 425 - 1180 µm	%	-	98 min.
Particle Size Distribution 425 - 850 µm	%	95 min.	-
Particle Size Distribution thr. 425 µm	%	1 max.	1.0 max.
Uniformity Coefficient	-	1.2 max.	1.2 max.
Ionic Conversion (⁷ Li ⁺)	eq%	99 min.	-
Ionic Conversion (Na ⁺)	eq%	0.1 max.	-
Ionic Conversion (OH ⁻)	eq%	-	95 min.
Ionic Conversion (CO ₃ ²⁻)	eq%	-	5 max.
Ionic Conversion (Cl ⁻)	eq%	-	0.2 max.
Metal Content (Ca)	mg/L	50 max.	50 max.
Metal Content (Pb)	mg/L	10 max.	10 max.
Metal Content (Fe)	mg/L	50 max.	50 max.
Metal Content (Cu)	mg/L	10 max.	10 max.
Water Extractables	g/L-R	0.5 max.	0.1 max.

Typical Properties

Component	Mixed resin	
Shipping Density	g/L	730

Recommended Operating Conditions

Maximum Operating Temperature	°C	60
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

