DIAION™ WA30C is a highly porous type weakly basic anion exchange resin. It is has tertiary amine functionality and low-leachable properties compared with DIAION™ WA30. A wide range of applications, especially in a field of higher purity water treatment application, is recommended.

P	ro	h	п	ct	
	1 ()	u	u	ι.ι	

Product						
Grade Name	ame DIAION <sup>TM</sup> WA30C					
Туре	Weak Base Anion					
Matrix	Matrix Styrene-DVB, High					
Functional Group		Tertiary Amine				
Ionic Form		Free Base				
Specification						
Whole Bead Count	-	95 min.				
Total Exchange Capacity	meq/mL	1.5 min.				
Water Content	%	43 - 55				
Particle Size Distribution on 1180 μm	%	5 max.				
Particle Size Distribution thr. 300 $\mu m$	%	1 max.				
Effective Size	mm	0.40 min.				
Uniformity Coefficient	-	1.6 max.				
COD	ppm	5 max.				
Typical Properties						
Shipping Density	g/L	650				
Mean Particle Size	μm	700				
Particle Density	g/mL	1.05				
Total Swelling (FB to Cl <sup>-</sup> )	%	23				
Recommended Operating Conditions						
Maximum Operating Temperature	°C	100				
Operating pH Range		0 - 9				
Minimum Bed Depth	mm	800				
Service Flow Rate	m/h	10 - 40				
Regenerant		NaOH				
Regenerant Concentration	%	NaOH 1 - 4				
Regenerant Level	% of ionic load	120				
Regenerant Flow Rate	m/h	2 - 6				
Total Rince Requirement	BV	5 - 10				



## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> WA30C resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of WA30C




Fig. 2 Bed Expansion of WA30C

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.



Phone: 212-204-0075 Email: info@pyvot.tech Web: www.puvot.tech