## **DIAION**<sup>™</sup> **PA312L**

DIAION™ PA312L is a porous type strongly basic anion exchange resin. It has a 6% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing pure water and waste water treatment, is recommended.

P	r۸	h	п	ct
1	ı	u	u	L.L

Product		
Grade Name		DIAION <sup>TM</sup> PA312L
Туре		Strong Base Anion
Matrix		Styrene-DVB, Porous
Functional Group	Type I	(trimethyl ammonium groups)
Ionic Form		Cl
Specification		
Whole Bead Count	-	95 min.
Salt Splitting Capacity	meq/mL	1.2 min.
Water Content	%	49 - 55
Particle Size Distribution on 1180 μm	%	5 max.
Particle Size Distribution thr. 425 $\mu m$	%	5 max.
Effective Size	mm	0.45 min.
Uniformity Coefficient	-	1.6 max.
Typical Properties		
Shipping Density	g/L	680
Mean Particle Size	μm	660
Particle Density	g/mL	1.07
Total Swelling (Cl to OH)	%	23
Recommended Operating Condit	ions	
Maximum Operating Temperature	°C	80 (Cl <sup>-</sup> )
		60 (OH <sup>-</sup> )
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8



g/L

m/h

BV

50 - 200

2 - 8

2 - 10

Regenerant Level

Regenerant Flow Rate

**Total Rince Requirement** 

## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> PA312L resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of PA312L




Fig. 2 Bed Expansion of PA312L

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

