## **Product Data Sheet**

## DIAION<sup>™</sup> PA418

DIAION™ PA418 is a porous type strongly basic anion exchange resin. It is type II resin and has a 9% cross-linkages. A wide range of applications, especially in a field of manufacturing pure water and waste water treatment, is recommended.

P	rod	uct
	ıou	uct

Grade Name		DIAION <sup>TM</sup> PA418	
Туре		Strong Base Anion	
Matrix		Styrene-DVB, Porous	
Functional Group	Type II (dim	ethylethanol ammonium groups)	
Ionic Form		Cl¯	
Specification			
Whole Bead Count	-	95 min.	
Salt Splitting Capacity	meq/mL	1.3 min.	
Water Content	%	38 - 44	
Particle Size Distribution on 1180 $\mu m$	%	5 max.	
Particle Size Distribution thr. 300 $\mu m$	%	1 max.	
Effective Size	mm	0.40 min.	
Uniformity Coefficient	-	1.6 max.	
Typical Properties			
Shipping Density	g/L	670	
Mean Particle Size	μm	710	
Particle Density	g/mL	1.11	
Total Swelling (Cl to OH)	%	11	
Recommended Operating Conditions			
Maximum Operating Temperature	°C	60 (Cl <sup>-</sup> )	
		40 (OH <sup>-</sup> )	
Operating pH Range		0 - 14	
Minimum Bed Depth	mm	800	
•			



m/h

%

g/L

m/h BV 10 - 60

NaOH

NaOH 2 - 8

50 - 200

2 - 8

2 - 10

Service Flow Rate

Regenerant Level

Regenerant Flow Rate

**Total Rince Requirement** 

**Regenerant Concentration** 

Regenerant

## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of  $\mathsf{DIAION}^\mathsf{TM}$  PA418 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of PA418




Fig. 2 Bed Expansion of PA418

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

