## **DIAION** PK216LH

DIAION™ PK216LH is a porous type strongly acidic cation exchange resin. It has 8% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water and catalysts, is recommended.

Р	ro	d	u	ct
	$\cdot$	u	u	·ι

Product			
Grade Name		DIAION <sup>TM</sup> PK216LH	
Туре		Strong Acid Cation	
Matrix		Styrene-DVB, Porous	
Functional Group		Sulfonic Acid	
Ionic Form		H <sup>+</sup>	
Specification			
Whole Bead Count	-	95 min.	
Salt Splitting Capacity	meq/mL	1.6 min.	
Water Content	%	50 - 60	
Particle Size Distribution on 1180 μm	%	5 max.	
Particle Size Distribution thr. 425 $\mu m$	%	1 max.	
Effective Size	mm	0.45 min.	
Uniformity Coefficient	-	1.6 max.	
Ionic Form Conversion H Form	eq%	95 min.	
Typical Properties			
Shipping Density	g/L	760	
Mean Particle Size	μm	750	
Particle Density	g/mL	1.19	
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	8	
Recommended Operating Condit	ions		
Maximum Operating Temperature	°C	120	
Operating pH Range		0 - 14	
Minimum Bed Depth	mm	800	
Service Flow Rate	m/h	10 - 60	
Regenerant		HCI	
		$H_2SO_4$	
Regenerant Concentration	%	HCl 4 - 10	
-		H <sub>2</sub> SO <sub>4</sub> 1 - 4	
Regenerant Level	g/L	50 - 200	
Regenerant Flow Rate	m/h	2 - 10	
Total Rince Requirement	BV	2 - 10	



## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> PK216LH resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of PK216LH




Fig. 2 Bed Expansion of PK216LH

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

