## **Product Data Sheet**

## DIAION<sup>™</sup> SK112L

DIAION™ SK112L is a gel type strongly acidic cation exchange resin. It has 12% cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Grade Name	DIAION <sup>™</sup> SK112L
Туре	Strong Acid Cation
Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid
Ionic Form	Na <sup>+</sup>

Specification		
Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	2.1 min.
Water Content	%	32 - 42
Particle Size Distribution on 1180 μm	%	5 max.
Particle Size Distribution thr. 425 $\mu m$	%	1 max.
Effective Size	mm	0.45 min.
Uniformity Coefficient	-	1.6 max.

Typical Properties		
Shipping Density	g/L	860
Mean Particle Size	μm	690
Particle Density	g/mL	1.34
Total Swelling (Na <sup>+</sup> to H <sup>+</sup> )	%	6

Recommended Operating Condit	ions	
Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 40
Regenerant		HCI
		$H_2SO_4$
Regenerant Concentration	%	HCl 4 - 10
		H <sub>2</sub> SO <sub>4</sub> 1 - 4
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	2 - 10
Total Rince Requirement	BV	2 - 10



## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of  $\mathsf{DIAION}^\mathsf{TM}$  SK112L resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of SK112L




Fig. 2 Bed Expansion of SK112L

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

