## **DIAION™ UBA1200HUP**

DIAION™ UBA120OHUP is an anion exchange resin with a uniform particle size. It has a standard cross-linkages and anti-clumping characteristics and excellent properties. It is recommended for higher purity water treatment application.

Product		
Grade Name		DIAION <sup>TM</sup> UBA120OHUP
Туре		Strong Base Anion
Matrix		Styrene-DVB, Gel
Functional Group	Тур	oe I (trimethyl ammonium groups)
Ionic Form		OH <sup>-</sup>
Specification		
Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	1.0 min.
Water Content	%	62 - 70
Mean Particle Size	μm	620 ± 50
Uniformity Coefficient	-	1.10 max.
Ionic Form Conversion (OH <sup>-</sup> )	eq%	90 min.
Ionic Form Conversion (Cl <sup>-</sup> )	eq%	1 max.
ΔΤΟC	ppb	20 max.
Outlet resistivity	MΩ•cm	15 min.
Typical Properties		
Shipping Density	g/L	655
Particle Density	g/mL	1.07
Total Swelling (Cl to OH)	%	24
Recommended Operating Condition	ions	
Maximum Operating Temperature	°C	80 (Cl <sup>-</sup> )
		60 (OH⁻)
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8
Regenerant Level	g/L	50 - 200
Regenerant Flow Rate	m/h	2 - 8



BV

2 - 10

**Total Rince Requirement** 

## **DIAION™ UBA1200HUP**

## **Hydraulic Characteristics**

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION<sup>TM</sup> UBA1200HUP resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBA120OHUP




Fig. 2 Bed Expansion of UBA120OHUP

## **Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.

